

Polytec EP 653

Properties

Polytec EP 653 is a 100% solid, two component, low viscosity, high temperature epoxy. The adhesive is certified to USP Class VI Biocompatibility Standards.

It was designed for medical, semiconductor, hybrid, piezo, fiber optics (such as medical endoscopes), HV and UHV applications. Polytec EP 653 has an excellent adhesion to glass, metal, ceramics, ferrite and most plastics. Recommended as adhesive, impregnation, underfill and encapsulation.

Polytec EP 653 passed > 500 autoclave steam cycles!

The material can be applied via dispensing, jet-dispensing and manual application.



Processing

- For two-component products the components A and B should be mixed carefully within the specified mixing ratio.
- For filled products both components should be homogenized carefully prior mixing, in order to prevent a possible settling of the filler.
- Processing should be carried out rapidly after mixing the components; as an indication the pot life can be used.
- Surfaces should be clean, thus free of dirt, grease, oil, dust or process chemicals.
- One-component products can be applied directly and are not subject to a pot life (except pre-mixed/frozen products).
- Please take notice of respective minimum curing temperature and time.
- For Safety information please refer to the respective Material Safety Data Sheet.

Polytec EP 653

Unfilled Epoxy Adhesive

Technical Data

Polytec EP 653

Properties in uncured state	Method	Unit	Technical Data
Chemical basis	-	-	Epoxy
No. of components	-	-	2
Mixing ratio (weight)	-	-	100:10
Mixing ratio (volume)	-	-	-
Pot life at 23°C	TM 702	h	24
Storage Stability at 23°C	TM 701	Months	12
Consistency	TM 101	-	Flowable liquid
Density Mix	TM 201.2	g/cm ³	1.10
Density A-Part	TM 201.2	g/cm ³	1.20
Density B-Part	TM 201.2	g/cm ³	1.05
Viscosity Mix 84 s ⁻¹ at 23°C	TM 202.1	mPa·s	6 000
Viscosity A-Part 84 s ⁻¹ at 23°C	TM 202.1	mPa·s	-
Viscosity B-Part 84 s ⁻¹ at 23°C	TM 202.1	mPa·s	-

Properties in cured* state	Method	Unit	Technical Data
Color	TM 101	-	Yellow/ amber
Hardness (Shore D)	DIN EN ISO 868	-	85
Temperature resistance continuous	TM 302	°C	-55 / +230
Temperature resistance short term	TM 302	°C	-55 / +300
Degradation Temperature	TM 302	°C	+400
Glass Transition Temperature (T _g)	TM 501	°C	+105
Coefficient of thermal expansion (<T _g)	ISO 11359-2	ppm	40
Coefficient of thermal expansion (>T _g)	ISO 11359-2	ppm	170
Thermal conductivity	-	W/m·K	-
Elasticity modulus	TM 605	N/mm ²	3 200
Permittivity	Ring Resonator	-	2.12
Loss factor	Ring Resonator	-	0.014
Tensile Strength	TM 605	N/mm ²	62
Lap shear strength (Al/Al)	TM 604	N/mm ²	-
Elongation at break	TM 605	%	2.8
Water absorption 24 h, 23°C	TM 301	%	0.24
Refractive index	-	-	-

*The above data has been determined with samples cured at 150°C. Please notice, by varying the curing temperature these properties can be influenced to some extend.

Polytec EP 653

Curing*	Method	Unit	Technical Data
Minimum curing temperature		°C	80
Curing time at 23°C		h	-
Curing time at 80°C		min	90
Curing time at 100°C		min	30
Curing time at 120°C		min	15
Curing time at 150°C		min	5
Curing time at 180°C		s	-

*Curing temperatures refer to the temperature in the respective bond line. When choosing the respective curing conditions, the time needed to heat the substrate has to be considered. Depending on the type of heat source (convection oven, hot stamp, heating plate) the heat input may vary.

Standard pack sizes:

250 g, 500 g

1 kg

Customized packaging

Please note:

The information listed above is typical data based on tests and is believed to be accurate. Polytec PT makes no warranties (expressed or implied) as to their accuracy. The data listed above does not constitute specifications. The processing (particularly the curing conditions) of the material, the process control, and the variety of different applications at various customers are not under Polytec PT's control. Therefore, Polytec PT will not be liable for concrete results in any specific application or in any connection with the use of this product. The curing conditions have a major effect on the properties of the cured material. Therefore, it is highly recommended to keep the curing schedule – once established - under tight control. With the release of this data sheet all former data sheets will be null and void.

Subject to alteration.

Polytec PT GmbH
 Polymere Technologien
 Ettlinger Straße 30
 76307 Karlsbad
 Germany
 Tel. +49 (0) 7243 604-4000
 Fax +49 (0) 7243 604-4200
 info@polytec-pt.de
 www.polytec-pt.de

Polytec PT GmbH
 Polymere Technologien
 plant Maxdorf
 Bahnhofstraße 1
 67133 Maxdorf
 Germany
 info@polytec-pt.de
 www.polytec-pt.de

Polytec France S.A.S.
 TECHNOSUD II
 Bâtiment A
 99, Rue Pierre Semard
 92320 Châtillon - France
 Phone. +33 (0)1 49 65 69 00
 Fax +33 (0)1 57 19 59 60
 info@polytec.fr
 www.polytec-pt.com